

Product Information

VESTAKEEP® 2000FP

Unreinforced, medium-viscosity polyether ether ketone fine powder

VESTAKEEP 2000FP is an unreinforced, medium-viscosity polyether ether ketone fine powder. It can be used as a basic resin or in blends with different additives for manufacturing compression molding parts.

The semi-crystalline polymer features superior thermal and chemical resistance. VESTAKEEP 2000FP is self-extinguishing

VESTAKEEP 2000FP is supplied as a powder in boxes with moisture-proof polyethylene liners.

For information about processing of VESTAKEEP 2000FP, please follow the general recommendations in our brochure "VESTAKEEP Polyether Ether Ketone."

For further information, please contact our experts in the department Market Development of the High Performance Polymers Business Line.

Powder Information

Property	Test method		Unit	VESTAKEEP 2000FP
	international	national		
App. bulk density	ISO 60	DIN 53 468	g/dm ³	280
Average particle size	d50	Malvern Mastersizer	µm	approx. 50

Application technology properties

Property	Test method		Unit	VESTAKEEP 2000FP	
	international	national			
Density	23°C	ISO 1183	DIN EN ISO 1183	g/cm ³	1.30
Tensile test		ISO 527-1	DIN EN ISO 527-1		
Stress at yield		ISO 527-2	DIN EN ISO 527-2	MPa	100
Strain at yield				%	5.5
Strain at break				%	20
Tensile modulus		ISO 527-1/2	DIN EN ISO 527-1/2	MPa	3600
CHARPY impact strength		ISO 179/1eU	DIN EN ISO 179/1eU		
	23°C			kJ/m ²	N ¹⁾
	-30°C			kJ/m ²	N ¹⁾
CHARPY notched impact strength		ISO 179/1eA	DIN EN ISO 179/1eA		
	23°C			kJ/m ²	6 C ¹⁾
	-30°C			kJ/m ²	6 C ¹⁾
Temperature of deflection under load		ISO 75-1	DIN EN ISO 75-1		
		ISO 75-2	DIN EN ISO 75-2		
Method A	1.8 MPa			°C	155
Method B	0.45 MPa			°C	205
Vicat softening temperature		ISO 306	DIN EN ISO 306		
Method A	10 N			°C	335
Method B	50 N			°C	310
Melting range		ISO 11357			
DSC	2 nd heating			°C	approx. 340
Melt volume-flow rate (MVR)		ISO 1133	DIN EN ISO 1133		
	380°C/5 kg			cm ³ /10 min	70
Flammability acc. UL94		IEC60695	UL94		
	0.8 mm				V-1
	1.6 mm				V-0

Pigmentation may affect values.

¹⁾ C = Complete break, incl. hinge break H
N = No break

® = registered trademark

This information and all further technical advice are based on Evonik Degussa's present knowledge and experience. However, Evonik Degussa assumes no liability for providing such information and advice including the extent to which such information and advice may relate to existing third party intellectual property rights, especially patent rights. In particular, Evonik Degussa disclaims all conditions and warranties, whether expressed or implied, including the implied warranties of fitness for a particular purpose or merchantability. Evonik Degussa shall not be responsible for consequential, indirect or incidental damages (including loss of profits) of any kind. Evonik Degussa reserves the right to make any changes according to technological progress or further developments. It is the customer's responsibility and obligation to carefully inspect and test any incoming goods. Performance of the product(s) described herein should be verified by testing and carried out only by qualified experts. It is the sole responsibility of the customer to carry out and arrange for any such testing. Reference to trade names used by other companies is neither a recommendation, nor an endorsement of any product and does not imply that similar products could not be used.

Evonik Degussa GmbH BL High Performance Polymers 45764 Marl Germany
Phone +49 2365 49-9878 Fax +49 02365 49-5992
www.degussa-hpp.com



EVONIK
INDUSTRIES