

## Product Information

### VESTAKEEP® M2G

**Medical grade; medium-viscosity, unreinforced polyether ether ketone**

VESTAKEEP M2G is a medium-viscosity, unreinforced polyether ether ketone for injection molding. The semi-crystalline polymer features superior thermal and chemical resistance. Parts made from VESTAKEEP M2G are self-extinguishing.

VESTAKEEP M2G can be processed by common machines for thermoplastics. We recommend a melt temperature between 680°F and 716°F during the injection molding process. The mold temperature should be within a range of 320°F to 392°F, preferably 356°F.

VESTAKEEP M2G is supplied as granules in 25 kg boxes with moisture-proof polyethylene liners.

For information about processing VESTAKEEP M2G please follow the general recommendations in our brochure "VESTAKEEP Polyether Ether Ketone Compounds".

**VESTAKEEP M2G fulfils the following requirements to meet the demands for medical applications:**

United States Pharmacopoeia Testing: <88> "Biological Reactivity Testing In Vivo" Class VI:

- Acute Systemic Toxicity test: 4 different extraction media (158°F/24h)
- Irritation Test – Intracutaneous Injection test: 4 different extraction media (158°F/24h)
- Implantation Test: In Vivo-Implantation test: intramuscular, 7 days

Biocompatibility testing:

- United States Pharmacopoeia Testing : <87> "Biological Reactivity Testing In Vitro"
- Cytotoxicity Test: L929 MEM elution, according to ISO 10993-5 (99°F/24h)

**For further information, please contact our experts in the department Market Development of the High Performance Polymers Business Line.**

Property	Test method		Unit	VESTAKEEP	Unit	VESTAKEEP
			SI	M2G	US	M2G
Density	73°F	ISO 1183	g/cm <sup>3</sup>	1.30	g/cm <sup>3</sup>	1.30
Tensile test		ASTM D638				
Stress at yield			MPa	100	kpsi	14.5
Strain at yield			%	5	%	5
Strain at break			%	30	%	30
Tensile modulus		ASTM D638	MPa	3700	kpsi	540
Flexural test		ASTM D790				
Flexural strength			MPa	145	kpsi	21
Flexural modulus		ASTM D790	MPa	3500	kpsi	510
CHARPY impact strength		ISO 179/1eU				
	73°F		kJ/m <sup>2</sup>	N <sup>1)</sup>	kJ/m <sup>2</sup>	N <sup>1)</sup>
	-22°F		kJ/m <sup>2</sup>	N <sup>1)</sup>	kJ/m <sup>2</sup>	N <sup>1)</sup>
IZOD notched impact strength		ASTM D256 A				
	73°F		J/m	52	ft-lb/in	1.0
	-22°F		J/m	50	ft-lb/in	1.0
Vicat softening temperature		ISO 306				
Method A	10 N		°C	335	°F	635
Method B	50 N		°C	310	°F	590
Linear thermal expansion		ISO 11359				
longitudinal	73-131°F		10 <sup>-4</sup> K <sup>-1</sup>	0.6	ppm/°F	33
Relative permittivity		IEC 60250				
	50 Hz			2.8		2.8
	1 MHz			2.8		2.8
Electric strength	K20/P50	IEC 60243-1	kV/mm	16	V/mil	406
Volume resistivity		IEC 60093	Ohm · m	10 <sup>15</sup>	Ohm · m	10 <sup>15</sup>
Surface resistance		IEC 60093	Ohm	10 <sup>14</sup>	Ohm	10 <sup>14</sup>
Melting range		ISO 11357				
DSC	2 <sup>nd</sup> heating		°C	approx. 340	°F	approx. 644
Melt volume-flow rate (MVR)		ISO 1133				
	716°F/ 5kg		cm <sup>3</sup> / 10 min	70	cm <sup>3</sup> / 10 min	70
Flammability acc. UL94		IEC 60695				
	0.06 inch	UL94		V-0		V-0
Glow wire test		IEC 60695-2-				
GWIT	0.08 inch	12/13	°C	875	°F	1607
GWFI	0.08 inch		°C	960	°F	1760
Mold shrinkage		0.08 inch				
in flow direction		sheets, mold-	%	0.7	%	0.7
in transverse direction		temp. 356°F	%	1.2	%	1.2
		ISO 294-4				

® = registered trademark

<sup>1)</sup> N = No break

This information and all technical and other advice are based on Evonik's present knowledge and experience. However, Evonik assumes no liability for such information or advice, including the extent to which such information or advice may relate to third party intellectual property rights. Evonik reserves the right to make any changes to information or advice at any time, without prior or subsequent notice. Evonik disclaims all representations and warranties, whether express or implied, and shall have no liability for, merchantability of the product or its fitness for a particular purpose (even if Evonik is aware of such purpose), or otherwise. Evonik shall not be responsible for consequential, indirect or incidental damages (including loss of profits) of any kind. It is the customer's sole responsibility to arrange for inspection and testing of all products by qualified experts. Reference to trade names used by other companies is neither a recommendation, nor an endorsement of the corresponding product, and does not imply that similar products could not be used.